# MICHELMAN

### DigiGuard® Gloss 110

**USAGE** DigiGuard<sup>®</sup> Gloss 110 is a high gloss, temperature resistant, water based overprint varnish which meets FDA food contact requirements.

### **DESCRIPTION** Overprint varnish for flexible packaging

PHYSICAL PROPERTIES

Appearance:	White, translucent liquid	
Non-Volatile (%):	38.0 - 40.0	
Brookfield Viscosity (cps):	< 200	
Spindle Number:	2	
RPM:	60	
pH:	8.0 - 10.0	

### SITE OF MANUFACTURE USA (DGG110), Belgium (DGG110.E) (and PRODUCT CODE)

APPLICATION DATA DigiGuard<sup>®</sup> Gloss 110 can be applied by flexo, gravure or roll coater. A drying temperature of 60C or above will ensuer optimum heat resistance of the coating is achieved.

Revised 08 September 2011

The following information for this product, specific to each site of manufacture, is available upon request:

• Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)

• Food Contact Declaration of Compliance

# MĪCHELMAN

## DigiGuard® Gloss 110

#### Americas Michelman Inc.

9080 Shell Road Cincinnati, Ohio 45236-1299 USA Tel: +1 513 793 7766

Fax: +1 513 793 2504

#### China

Michelman (Shanghai) Chemical Trading Co., Ltd. Room 212, Building 3 Zhongtian Science Technology Park No. 787 Kangqiao Road Shanghai, China 201315

Tel: +86 21 2098 6880 Fax: +86 21 2098 6881 Europe, Middle East, Africa Michelman SARL 11, rue de l'Industrie L-8399 Windhof Luxembourg Tel: +352 26 39 44 1 Fax: +352 26 39 44 80

India Michelman Chemicals Pvt.Ltd.

Fax: +91 22 28672784

C/O Mehta Paper Industries, First Floor, Plot NO 61CD, Government Industrial Estate, Charkop, Kandivali (West) Mumbai-400 067 India Tel: +91 22 28672783 Asia Pacific Michelman Asia-Pacific Pte. Ltd. 2A Tuas Avenue 12 Singapore 639023

Tel: +65 6861 2822 Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. For the same reason, the products discussed are sold without warranty, express or implied and on the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement. © 2014 MICHELMAN, INC. All rights reserved.

All marks contained herein are registered or owned by Michelman, Inc. Michelman is ISO 9000 certified.