



Sunset Fibre Elite 285g

Sunset Fibre Elite is a second generation fibre-based material that is both super-smooth and very high gloss. It was developed in response to requests from photographers searching for a smoother version of the 2007 PPA Hot One Award-winning Sunset Fibre Gloss. Like the Fibre Gloss, Elite is modeled after the traditional fibre-based materials used in a conventional darkroom for a high-end, classic look and feel. It is available in a 285g microporous high gloss coated surface with a special acid inhibiting layer, thus making it the perfect inkjet alternative. It is designed for fine photographic reproduction of the highest quality.

Property	Specifications
Material	Bright white, smooth, microporous gloss
Gauge	14 mil
Opacity	94.95%
pH Value	7.9-8.5
Whiteness	94.1%
Printer Ink/Compatibility	Optimized for use on all Epson Series Ultrachrome printers, Canon Lucia, and HP Vivera ink sets.
Software Settings	The coating on this product is engineered for better than 300% ink coverage. A luster, or glossy paper setting is the appropriate starting point. However, we recommend that you try different settings to achieve optimum performance for your specific application.
Color Matching	For the best and most consistent results, a profile should be created using an external color calibrator in conjunction with your RIP and/or color matching software.
Light Fastness	The fading time of inkjet ink is a direct result of the inks that you choose, as well as the environment where the print is displayed. Although the fading process is inherent in all inkjet inks, certain UV-enhanced inks, pigment-based inks, and UV-inhibiting coatings will extend the longevity of ink color. Contact the ink manufacturer to determine a specific ink's suitability for a particular application. LexJet's Sunset line of fibre-based materials all meet the Fine Art Trade Guild Standards for Limited Edition Prints (otherwise known as the Blue Wool 6 test).
Finishing/Post Processing	No post processing or finishing is required on this paper. However, a clear fixative may be applied to enhance certain areas of the print. We recommend 24 hours before putting behind glass.
Optimal Service Environment	For printing: 68-77° F, 20-60% Relative Humidity. For end use: 0-300° F
Handling Recommendations	Due to the absorptive nature of the coating, you should avoid touching the coated surface of the paper. It is always recommended that cotton gloves be used when handling inkjet coated materials. Rolls of LexJet Sunset media are supplied with the coated side facing out.
Ideal Storage Conditions	70°F (21°C); 50% R.H.; store in original packaging; a controlled environment is recommended.
Shelf Life	Greater than 1 year from the LexJet ship date when stored in proper conditions.

Product Performance & Suitability: All of the descriptive information and recommendations for the use of LexJet products should be used only as a guide. Furnishing such information and recommendations shall in no event constitute a warranty of any kind by LexJet. All purchasers of LexJet products shall independently determine the suitability of the material for the purpose for which it is purchased. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither the seller nor manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential (including loss of profits or revenue) arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in agreement signed by officers of seller and manufacturer.