

Avery Dennison® IC MPI 2900 / 2902 / 2903 Gloss

Permanent / Removable StaFlat™

(formerly: MPI 3100 / 3101/ 3103)

Revision: 9 Dated: 12/02/13

Uses:

Avery Dennison® IC MPI 2900, 2902, and 2903Gloss are flexible calendered vinyl films. IC MPI 2900, 2902, and 2903 Gloss offer exceptional value for applications requiring a glossy mid-term durable product combined with a permanent or removable adhesive. IC MPI 2900, 2902, and 2903 Gloss films are well suited for applications such as Point-of-Purchase, Product Identification Labels, Medium Term OEM Decals as well as Outdoor and General Signage.



Face: 3.0 mil (76 microns) high gloss calendered



Adhesive: Acrylic
MPI 2900 – Perm (clear)
MPI 2902 – Rem (gray)
MPI 2903 – Perm (gray)



Liner: 90# StaFlat™



Durability: Up to 5years (unprinted)

Application Surfaces:

Flat, simple curves (restricted to non-spill areas)

Features:

- Gray adhesive provides opacity to covers whatever is underneath
- Gloss finish
- Good durability and outdoor performance for short to mid-term applications
- Great image clarity and color pop
- ICC profiles available on *the Avery Dennison* website (www.iccprofiles.averygraphics.com)

Conversion:

- Thermal Die-Cutting
- Flat Bed Sign-Cut
- Drum Roller Sign-Cut
- Steel Rule Die-Cutting
- Solvent based inkjet
- Mild/Eco Solvent inkjet
- UV inkjet
- Latex Inkjet

Common Applications:

- Fleet (flat & simple curve only)
- Vehicle (flat & simple curve only)
- Wall Murals
- POP/ Tradeshow
- Outdoor Signage
- Floor Graphics
- Ice Rink Boards /Dasher Boards

Product Data Sheet

Page 1 of 3



Graphics and Reflective Solutions

averygraphics.com
AnswerLine: 800-231-4654

Avery Dennison® IC MPI 2900 / 2902 / 2903 Gloss

Permanent / Removable StaFlat™

(formerly: MPI 3100 / 3101/ 3103)

Revision: 9 Dated: 12/02/13

Physical Characteristics:

Property		Value
Caliper, face		3.0 mil (76µm)
Caliper, adhesive		1.0mil (25 µm)
Dimensional stability		<0.065"(1.651 mm)
		Note: Ink loads in excess of 250% may cause increased shrinkage of the printed film.
Tensile at Yield		
Elongation		
Gloss	Hunter Gloss @ 60	90 ±10
<u>Adhesion: 15 min.</u>	<u>Adhesive</u>	
MPI2900	Perm (clear)	4.7 lbs/in (831 N/m)
MPI2902	Rem (gray)	2.5 lbs/in (438 N/m)
MPI2903	Perm (gray)	5.5 lbs/in (962 N/m)
<u>Adhesion: 24 hr</u>	<u>Adhesive</u>	
MPI2900	Perm (clear)	5.5 lbs/in (962 N/m)
MPI2902	Rem (Gray)	5.4 lbs/in (945 N/m)
MPI2903	Perm (Gray)	5.5 lbs/in (962 N/m)
Removability	MPI 2902	3 years from most substrates. Surface must be sealed.
Flammability		Self Extinguishing
Shelf-Life		<i>2 years from date on label (up to 2 years unprocessed, OR process within one year and apply within 1 year of processing)</i>
Durability	Vertical Exposure	Unprinted – 5 years Printed – Up to 3 years
Min. Application Temperature		50° F (10° C)
Service Temperature		-40° - 180°F (-40° - 82° C) (Reasonable range of temperatures which would be expected under normal environmental conditions).
Chemical resistance		Resistant to most mild acids, alkalis, and salt solutions.

Important:

Information on physical and chemical characteristics are based on tests believed to be reliable. The values are intended only as a source of information. This information is given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of any material for their specific purpose. (Data represents average values where applicable, and is not intended for specification purposes)

Warranty:

All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either two years (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.

Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.

NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.

Product Data Sheet

Page 2 of 3



Graphics and Reflective Solutions

averygraphics.com
AnswerLine: 800-231-4654

Avery Dennison® IC MPI 2900 / 2902 / 2903 Gloss

Permanent / Removable StaFlat™

(formerly: MPI 3100 / 3101/ 3103)

Revision: 9 Dated: 12/02/13

Dimensional stability:

Is measured on a 6" x 6" (150 x 150 mm) aluminum panel to which a specimen has been applied; 72 hours after application the panel is scored in a cross pattern, exposed for 48 hours to 150°F (65°C), after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel panel, 24 hours after the specimen has been applied under standardized conditions. Initial adhesion is measured 15 minutes after application of the specimen.

Removability:

Avery Dennison® does not guarantee removability from the following substrates:

- Surfaces with poor paint-to-substrate adhesion
- Wallboard
- Existing graphics that must remain intact; damage to existing graphic when film is removed
- Aged paint or metal that may have surface oxidation or chalking
- Outdoor, horizontal surfaces

Flammability:

A specimen applied to aluminum is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Revisions are italicized

Avery Dennison is a registered trademark of Avery Dennison Corp.

Product Data Sheet

Page 3 of 3



Graphics and
Reflective Solutions

averygraphics.com
AnswerLine: 800-231-4654